

**PRODUCT
DATA SHEET**

SL-520C

Physical Properties

Color	Green
Density	11.00 lbs/gal
Odor	Neutral
Shelf Life	24 months
Grab Time Cure Time Full Cure Time <small>@ 77 F And 50 relative humidity</small>	15 minutes 20 minutes 24 Hours
Solvents	NONE
VOCs	NONE
Solids	100%
Viscosity	> 30,000 cps



SL-500 Installation Kit



SL-520C Cartridge



SL-520C Performance Properties

(Seam Rip Test Aged and non-aged samples)

Temperature (° F)	Average Force Applied	Average Applied Force (Aged)
77°	313 PSI	318

MARCH 2011

Exclusively Distributed by:

Engineered Sportfield Solutions, LLC

info@engineeredsportfield.com

4223 Rock Run Road, Havre de Grace, MD 21078

Phone: 410-878-6341 Fax: 410-734-4129

